




CRANES & INDUSTRIAL WIRE ROPE

CONSTRUCTEX

Constructex is produced by rotary swaging a completed rope after manufacture. This swaging process reduces the rope diameter and reforms the profile of the outer strands, providing a rope that performs excellent in multilayer drum applications.

- Excellent service life in the most demanding applications
- Robust crush resistant rope construction
- Recommended for multi-layered spooling
- Improved wear characteristics



CONSTRUCTEX

BRIDON · BEKAERT
THE ROPES GROUP

Diameter		Nominal length mass		Minimum Breaking Force CTX		
mm	inch	kg/m	lb/ft	kN	Tons (short)	Tonnes (metric)
	5/8	1.34	0.900	227	25.5	23.1
16.0		1.34	0.900	227	25.5	23.1
19.0		1.64	1.102	325	36.5	33.1
	3/4	1.64	1.102	325	36.5	33.1
22.0		2.23	1.498	432	48.6	44.1
	7/8	2.23	1.498	432	48.5	44.1
	1	2.98	2.002	556	62.5	56.7
	1 1/8	3.87	2.601	707	79.5	72.1
	1 1/4	4.76	3.199	868	97.6	88.5
32.0		4.76	3.199	868	97.6	88.5
	1 3/8	5.66	3.803	1060	119	108
38.0		6.85	4.603	1240	139	126
	1 1/2	6.85	4.603	1240	139	126
	1 5/8	7.89	5.302	1440	162	147
44.0		9.23	6.202	1650	185	168
	1 3/4	9.23	6.202	1650	185	168